

# CLASSIC ROOF TILE



**Boston Valley  
Terra Cotta**

1.888.214.3655 [www.BostonValley.com](http://www.BostonValley.com)

6860 South Abbott Rd • Orchard Park, NY 14127  
TEL 716.649.7490 FAX 716.649.7688

# CLASSIC ROOF TILE



MEDITERRANEAN SERIES  
**Greek Pan/Cover**



MEDITERRANEAN SERIES  
**Spanish "S"**



CRAFTSMAN SERIES  
**Jumbo**



CRAFTSMAN SERIES  
**Appalachian**

## Custom Shapes and Colors

Roof tiles and fittings are available in a wide range of shapes and colors, including custom options, to meet the needs of nearly any architectural project. Please see our website, [www.bostonvalley.com](http://www.bostonvalley.com), or call 888-214-3655 for additional information.



## Recreating The Past Shaping The Future

As a leader in the manufacture of architectural terra cotta, Boston Valley continues the legacy of recreating the past and shaping the future with classic roof tile for historic restoration, replication and new construction. Our team specializes in custom projects, providing assistance through decades of experience.

Boston Valley Terra Cotta maintains a reputation as an internationally respected producer of quality clay products. Our Grade 1 terra cotta roof tile product line is crafted in a unique array of profiles, colors and finishes. Boston Valley also produces custom tiles for replication of rare or unique shapes.

### Warranty

Boston Valley Terra Cotta roof tiles are guaranteed to be free of defects in workmanship. For Grade 1 roof tile, we warrant that the quality of the material will not impair function for a period of 75 years.\*

*\*Some roof accessories and fittings are considered terra cotta components and carry a 10 year warranty.*

### Technical Data & Specifications

Boston Valley Terra Cotta manufactures a Grade 1 terra cotta roof tile. Data is based on an average of 5 tiles.

WEATHER INDEX  
500 and greater

TRANSVERSE BREAKING STRENGTH  
TYPE I – High Profile Average 400 lbf (N)  
TYPE II – Low Profile Average 300 lbf (N)

ABSORPTION RATE  
Average not greater than 6%

SATURATION COEFFICIENT  
Average is .74